

**KAYA PLASTIK BRANDA  
SAN.TIC.LTD.STI  
FEVZPASA MAH. SOGUT CAD NO:7  
DEGIRMENKOY / SILIVRI / ISTANBUL  
TURKEY**



**Your notice of** 07-03-2013  
**Your reference**  
**Date** 26-03-2013

**Analysis Report 13.01133.02**

Required tests :

**DIN 4102-1B2 (1998)**

**Burning behaviour - B2**

Identification number	Information given by the client	Date of receipt
T1303630	Reference: FL 85 / AS- 180 Test specimen: PES fabric PVC coated on both sides Quality: DENIER 700 g/m <sup>2</sup> TARPAULIN Manufacturer: KAYA PLASTIK BRANDA SAN.TIC.LTD.STI	07-03-2013

Pros Van Hoeyland

Order responsible

This report runs to 2 pages and may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.

The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

**VAT BE 0459.218.289**

**Fin. Acc. 210-0472965-45**

**IBAN BE44 2100 4729 6545**

CENTEXBEL-GENT  
Technologiepark 7  
BE-9052 Zwijnaarde  
Tel. + 32 9 220 41 51 • Fax + 32 9 220 49 55  
gent@centexbel.be

CENTEXBEL-VERVIERS  
Avenue du Parc 38  
BE-4650 Herve (Chaineux)  
Tel. + 32 87 32 24 30 Fax + 32 87 34 05 18  
chaineux@centexbel.be

**Reference:** T1303630 - **Reference:** FL 85 / AS- 180  
**Test specimen:** PES fabric PVC coated on both sides  
**Quality:** DENIER 700 g/m<sup>2</sup> TARPAULIN  
**Manufacturer:** KAYA PLASTIK BRANDA SAN.TIC.LTD.STI

**Burning behaviour - B2**

Date of ending the test 25-03-2013  
 Standard used DIN 4102-1B2 (1998)

Deviation from the standard -

Conditioning 23°C, relative humidity 50%

Ignition Surface

**Length**

		2	3	4	5
Time to reach 150 mm mark (s) °	*	*	*	*	*
Ignition filter paper within 20 s after flame application	no	no	no	no	no

° tip of the flame

\* = time to reach the mark > 20 s or mark not reached

**Width**

	1	2	3	4	5
Time to reach 150 mm mark (s) °	*	*	*	*	*
Ignition filter paper within 20 s after flame application	no	no	no	no	no

° tip of the flame

\* = time to reach the mark > 20 s or mark not reached

**Criteria**

- time to reach the mark > 20 s for all test specimens

**Conclusion B2**