



## TEST REPORT

Page 1 of 2

**REPORT NUMBER :** TURA140146003  
**APPLICANT NAME :** Kaya Plastik Branda San. Tic. Ltd. Şti.  
**ADDRESS :** Fevzipaşa Mah. Söğüt Cad. No:7 DeğirmenköySilivri İstanbul / TURKEY  
 TEL:0212 735 39 40FAX:0212 735 39 37

**Attention :** Şaban Kahraman ( [saban@kayaplastik.com.tr](mailto:saban@kayaplastik.com.tr) )

**SAMPLE DESCRIPTION :** One sample of Grey 1000 Deuier Tarp 2X

**DATE IN :** 24 September ,2014 ( 9:42)

**DATE OUT :** 24 September ,2014

**NOTE :** In this test report sample test results were taken from report no TURA140143119 by the request of vendor.

TEST	SAMPLE
Phthalate Content	1 P


P = MEETS BUYER' S REQUIREMENT / F = DOES NOT MEET BUYER' S REQUIREMENT / NR = NO REQUIREMENT / SC=STILL CONTINUES / X=NOT PERFORMED / NA = NOT APPLICABLE / LS = LACK OF SAMPLE / NC = NO COMMENT / I = INCONCLUSIVE

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>.

The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and TÜRKAK accreditation requirements. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered. When uncertainty is taken into account, the result may be borderline. Borderline results need to be re-tested to determine their disposition up to customer's decision. Opinions and interpretations expressed herein are outside the scope of TÜRKAK accreditation. Tests marked (\*) in this test report are not included in the TÜRKAK accreditation schedule for this laboratory.



Aşkın GÜNERİ  
COORDINATOR



Neslihan Sözer  
Chemical Laboratory Manager



**Intertek Test Hizmetleri A.S.**  
 Merkez Mahallesi Sanayi Cad. No.23 Altındag Plaza Yenibosna-34197 /İSTANBUL

Phone : +90 212 496 46 46 Fax: +90 212 452 80 55

e-mail : [intertekcg.turkiye@intertek.com](mailto:intertekcg.turkiye@intertek.com)

<http://www.intertek-turkey.com>



140146003

Test Method	Results	Requirements
-------------	---------	--------------

## Phthalate Content

INTERTEK IHTM AL.2.026 based on EN 14372 : 2004

Method By Gas Chromotography- Mass Spectrometry (GC- MS ) Analysis

	RESULT (% , w/w)
DIBUTYL PHTHALATE (DBP)	ND
DIETHYL HEXYL PHTHALATE (DEHP)	343 ppm
BENZYL BUTYL PHTHALATE (BBP)	ND
SUM OF THREE PHTHALATES	343 ppm
LIMIT (MAX.)	TOTAL 0.1% (1000 ppm)
DI-ISO-NONYL PHTHALATE (DINP)	ND
DI-N-OCTYL PHTHALATE (DNOP)	ND
DI-ISO-DECYL PHTHALATE (DIDP)	ND
SUM OF THREE PHTHALATES	ND
LIMIT (MAX.)	TOTAL 0.1% (1000 ppm)

**REMARK** =The Limit of 0.1% by weight was quoted according to Annex XVII Items 51&52 of the REACH Regulation (EC) No.1907/2006 (Formerly known as Directive 2005/84/EC) for Phthalate Content

**ppm (part per million) =mg / kg < =Less Than \* =EXCEEDED LIMIT ND = NOT DETECTED**  
**DETECTION LIMIT : DINP, DIDP : 100 ppm, Other Phthalates : 10 ppm**

**Estimated Total Uncertainty=( ±5%)**

## END OF TEST REPORT ##



**Intertek Test Hizmetleri A.S.**

*Merkez Mahallesi Sanayi Cad. No.23 Altindag Plaza Yenibosna-34197 /ISTANBUL*

*Phone : +90 212 496 46 46 Fax: +90 212 452 80 55*

*e-mail : intertekcg.turkiye@intertek.com*

<http://www.intertek-turkey.com>